



Korotek Boya ve Kimya San.Tic.Ltd.Şti.

Akse Mahallesi 535. Sokak
No 11 Çayırova 41420
Kocaeli Türkiye

Tel: +90 262 744 0254
Fax: +90 262 744 19 54

info@korotekkimya.com
www.korotekkimya.com

QUV test result of VASTCOAT MT products testing in KOROTEK R&D laboratory is as follows:

Date: 10.12.2013

Subject: QUV test results of Vastcoat MT color products

Standard	ASTM D-4587
Conditions	Cycle changes every 4 hours: 1. cycle: 50°C- 0,67 W/m ² UV 2. cycle: 40°C humidity
Testing period	2000 hours

Name of product	ΔE	% Gloss Retention	Lifetime (years)
VASTCOAT MT Ral 1021 Yellow	2.94	72	30-35
VASTCOAT MT Ral 2008 Orange	1.02	86	30-35
VASTCOAT MT Ral 3020 Red	0.97	96	30-35
VASTCOAT MT Ral 5015 Blue	1.68	68	30-35
VASTCOAT MT Ral 5017 Blue	0.91	103	30-35
VASTCOAT MT Ral 6005 Green	1.53	96	30-35
VASTCOAT MT Ral 7016 Grey	1.09	104	30-35
VASTCOAT MT Ral 7035 Grey	0.57	86	30-35
VASTCOAT MT Ral 9005 Black	1.67	105	30-35
VASTCOAT MT Ral 9006 Metallic Grey	0.07	128	30-35
VASTCOAT MT Ral 9016 White	0.32	114	30-35